



European
Ceramics

CIVIC RANGE

Product Name: **CIVIC - VARIOUS COLOUR/FINISHES**

Product Identifier: Refer to tile name and product code on paperwork/packaging

Product Description: A glazed porcelain tile and a water absorption rate of less than 0.50%.

Country Of Origin: Italy

Building Code Obligations

Code Clauses:

B2 – Durability

B2.3.1

C3 – Fire affecting areas beyond the
source

D1 – Access routes

D1.3.3

E3 – Internal moisture

E3.3.2, 3.3.3, 3.3.4

G3 – Food preparation and prevention of
contamination

G3.3.2

G6 – Airborne and Impact sound

G6.3.1



Note – this building product is not subject to a warning/ban under section 26 of the Building Act 2004

Manufacturer Details:

European Ceramics Approved

BPIR COMPLIANT

Importer Details:

European Ceramic Tiles Ltd

Address: 7A Cowley Place, Rosedale, AKL 0632

NZBN: 9429037294571

Website: euroceramics.co.nz

Scope	Use
B2 Durability	See below suitability table
C3 Fire	The Building Code relating to fire ratings regulation & standards become mandatory from April 2013, establishing the list of products belonging to Classes A 'No Contribution to Fire' provided for in Decision 94/611/EC implementing Article 20 of Council Directive 89/106/EEC.
D1 Access Routes	Refer to slip resistance documentation for all Access routes classifications D1/AS1 for above range.
E3 Internal Moisture	Under E3 Tiles installed over a waterproof membrane using a nonporous grouting system, are an acceptable solution.
G3 Food Preparation & Prevention from Contamination	As an impervious and easy to clean surface, this range complies.
G6 Airborne & Impact Sound	If required, tiles can form part of an acoustic system to comply with IIC & STC in conjunction with an approved third-party system.

<i>Suitability *</i>	<i>Residential</i>	<i>Light Commercial</i>	<i>Commercial</i>
Indoor Floor	*	*	*
Indoor Walls	*	*	*
Outdoor Cladding	*	*	*
Frost Resistant	*	*	*
Swimming Pool Submerged	*	*	*
Swimming Pool Surround	*	*	*
Paving/External	*	*	*
Over Underfloor Heating	*	*	*
Kitchen wall	*	*	*
Within 1.5m of a Plumbing Fixture or Fitting	*	*	*

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz

Building Code References

B2 – Durability

Compliance with B2 Durability is about providing evidence that the product will meet the relevant durability life in the context of the environment in which it will be located.

The building code sets out the framework for establishing the relevant durability life of building elements based on a number of criteria. B2/AS1 provides a decision tree to establish the relevant durability for common building materials in different circumstances.

Having determined the durability life of the product, the next step is to determine if the product, when exposed to the environment, will continue to perform for the relevant period. A key tool which a product supplier can consider in claiming compliance is limiting the environment in which the product will be exposed to (e.g. a ferrous material used in an indoor environment will last longer than it would when exposed to salt spray — in this example it would be appropriate for the supplier to condition the compliance information to use only in indoor environments).

C3 – Fire affecting areas beyond the source

C3 Fire affecting areas beyond the fire source is primarily about ensuring that fire does not spread from a fire in the building (in both vertically and horizontally) and from an adjacent building.

The prime product attribute used is the fire resistance rating (FRR) methodology. In most cases a product is combined with other products to achieve a FRR (e.g. an external wall fire rating may be formed by the combination of the external cladding, thermal insulation and the internal lining).

C/AS1 and C/AS2 set out performance criteria for buildings and in particular the FRR requirements for various types of buildings and parts of buildings. Appendix C of C/AS2 sets out test methods for the building elements involved in spread of fire. Appendix B of C/AS2 sets out performance criteria for sprinkler systems while Appendix A sets out criteria for fire safety systems such as alarms and hydrants.

D1 – Access routes

For D1 access routes, in most cases product-related compliance for access routes is slip resistance for floors and the shapes/locations etc of handrails. The Acceptable Solution for access D1/AS1 and NZS 4121:2001 provide good information on compliance for products on access routes.

E3 – Internal Moisture

E3 Internal Moisture is about ensuring that moisture created within the building does not lead to mould or create damage to adjacent buildings or structural elements in the building in which it is installed.

Prevention of the creation of mould is a combination of temperature, insulation and ventilation. Prevention of water damaging other building elements is mainly about installation details (i.e. sealing joints) as well as impervious products. E3/AS1 provides some useful design details, albeit without much product material information.

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz

G3 – Food preparation and prevention of contamination

G3 Food preparation and prevention from contamination for a product (such as a kitchen bench) is mainly associated with being easily cleaned and impervious. G3/AS1 provides some general design details for food preparation areas but has no referenced product standards, although the document does state some acceptable materials used for surfaces. Compliance with G3/AS1 is not mandatory but provides a good benchmark for compliance.

G6 – Airborne and Impact Sound

For a product, G6 Airborne and impact sound is generally about systems which are designed to work together to achieve the necessary sound attenuation.

The code itself at G6.3.2 sets a quantifiable performance level: “The Sound Transmission Class of walls, floors and ceilings, shall be no less than 55” and G6.3.2 sets the impact insulation class of floors shall be no less than 55. The Acceptable Solution G6/AS1 sets out the transmission and impact insulation class of common wall systems. G6/VM1 sets out test methodologies where the details do not match those of G6/AS1.

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz

Technical Information

Cross		120x120 cm 47 1/4" x 47 1/4" 9 mm Matt TP RT R10 B	60x120 cm 23 1/2" x 47 1/4" 9 mm Matt TP RT R10 B	Grip TP RT R11 C	80x80 cm 31 1/2" x 31 1/2" 9 mm Matt TP RT R10 B	60x60 cm 23 1/2" x 23 1/2" 9 mm Matt TP RT R10 B	30x60 cm 11 3/4" x 23 1/2" 9 mm Matt TP RT R10 B	120x120 cm 47 1/4" x 47 1/4" 20 mm Aextra20 RT R11 C	60x120 cm 23 1/2" x 47 1/4" 20 mm Aextra20 RT R11 C	60x60 cm 23 1/2" x 23 1/2" 20 mm Aextra20 RT R11 C
	Fusion	•	•	•	•	•	•			
	Sable	•	•	•	•	•	•	•	•	•
	Clear	•	•	•	•	•	•			
	Plinth	•	•	•	•	•	•	•	•	•
	Silent	•	•	•		•	•			

Vein		120x278 cm 47 1/4" x 109 1/2" 6 mm Matt RT R9	60x120 cm 23 1/2" x 47 1/4" 9 mm Matt TP RT R10 B
	Fusion		•
	Sable	•	•
	Clear	•	•
	Plinth	•	•
	Silent		•

Chips		120x120 cm 47 1/4" x 47 1/4" 9 mm Matt TP RT R10 B	60x60 cm 23 1/2" x 23 1/2" 9 mm Matt TP RT R10 B	60x60 cm 23 1/2" x 23 1/2" 20 mm Aextra20 RT R11 C
	Fusion	•	•	
	Sable	•	•	•
	Clear	•	•	
	Plinth	•	•	•
	Silent	•	•	

Multicolor		60x60 cm 23 1/2" x 23 1/2" 9 mm Matt TP RT R10 B	30x30 cm 11 3/4" x 11 3/4" 9 mm Matt TP RT R10 B
	Warm	•	•
	White	•	•
	Cold	•	•
	Black	•	•

TP TOUCH PLUS

Superfici che coniugano una gradevole sensazione al tatto con specifiche performance di resistenza allo scivolamento. - Surfaces that combine a pleasant tactile sensation with specific anti-slip properties. - Das surfaces qui associent une agréable sensation au toucher et des performances spécifiques de résistance au glissement. - Beläge, die eine angenehme Haptik mit spezifischer Rutschfestigkeit vereinen. - Поверхности, сочетающие приятные тактильные ощущения с особыми противоскользящими свойствами.

RT Rettificato, squadrato, monocolor. - Rectified, squared, one caliber. - Rectifié, mis d'éguaire et monocolor. - Rektifiziert, rechteckig und Ein kaliber. - Ректифицированный, одного калибра.
 ** Disponibile solo su richiesta. - Manufactured only upon special request. - Seulement sur demande. - Nur auf Anfrage. - Производится только по заказу.

Si raccomanda l'utilizzo di una fuga di 2/3 mm al fine di semplificare le operazioni di posa e ottimizzare la naturalezza del risultato finale. - We recommend you a 2/3 mm grout joint to simplify the laying and optimize the naturalness of the final result. - Un joint de 2/3 mm est conseillé afin de simplifier les opérations de pose et optimiser l'effet naturel du résultat final. - Es wird empfohlen mit einer Fuge von 2/3 mm zu arbeiten, um am Ende den Verlegevorgang zu vereinfachen und die bestmögliche Natürlichkeit der Arbeit zu erzielen. - Для облегчения операций укладки и повышения натуральности вида конечного результата рекомендуется выполнять шов шириной 2-3 мм.

Al fine di facilitare la manutenzione ordinaria si raccomanda di effettuare un lavaggio acido dopo 48 ore dalla stuccatura con un acido specifico per grès porcellanato. - In order to favour the ordinary maintenance procedures, it is recommended to carry out an acid wash of the surface after 48 hours from grout filling using an acid agent specific for porcelain stoneware tiles. - Afin de faciliter l'entretien ordinaire de votre carrelage, nous vous conseillons de le laver 48 heures après le colmatage des joints, avec un acide spécifique pour grès cérame. - Um die Instandhaltung zu erleichtern, empfiehlt es sich 48 Stunden nach der Stuckatur mit einer sauren Lösung speziell für Feinsteinzeug zu waschen. - Чтобы упростить уход за плиткой, спустя 48 часов после затирки швов рекомендуется выполнить обработку кислотным продуктом, пригодным для керамогранита.

CIVIC

72

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz

		 Battiscopa - Bullnose Plintha - Sockel Plinthylo 7,2x60 cm 2 7/8"x2 3/8"x1/8" Matt TP	 Scalino - Step tread Nez de marche - Stufe Cotto-Art Фартисауер ступене 33x120 cm 13"x47 1/2"x1/4" Matt TP	 Scalino - Step tread Nez de marche - Stufe Cotto-Art Фартисауер ступене 33x60 cm 13"x23 1/2"x1/4" Matt TP	 Angolare - Step tread corner Pice angolare - Stufenacke Угловая ступене 33x33 cm 13"x13" Matt TP	Angolare	Angolare SX	Angolare DX
Cross	Fusion	●	●	●	●			
	Sable	●	●	●	●			
	Clear	●	●	●	●			
	Plinth	●	●	●	●			
	Silent	●	●	●	●			
Vein	Fusion		●			●		●
	Sable		●			●		●
	Clear		●			●		●
	Plinth		●			●		●
	Silent		●			●		●
Chips	Fusion	●	●	●	●			
	Sable	●	●	●	●			
	Clear	●	●	●	●			
	Plinth	●	●	●	●			
	Silent	●	●	●	●			

· Imballi · Packaging · Conditionnement · Verpackungs · Упаковка

Formato - Size - Format - Формат		Scatola - Box - Boîte - Karton - Коробка			Pallet - Palette - Палета		
Cm	Inches	Pz	Mq	Kg	Sc	Mq	Kg
120x278	47 1/8"x109 7/8"	1	3,3221	~49,56	18	59,79	~892,08
120x120	47 1/8"x47 1/8"	2	2,856	~62,00	20	57,12	~1240,00
60x120	23 1/8"x47 1/8"	2	1,44	~30,40	36	50,40	~1064,00
80x80	31 1/8"x31 1/8"	2	1,28	~27,36	48	61,44	~1313,28
60x60	23 1/8"x23 1/8"	4	1,44	~28,00	30	43,20	~840,00
30x60	11 3/8"x23 1/8"	7	1,26	~25,00	40	50,40	~1000,00
30x30	11 3/8"x11 3/8"	12	1,08	~21,30	48	61,84	~1022,40
120x120 A E X T R A 2 0	47 1/8"x47 1/8"	1	1,44	~65,50	20	28,80	~1310,00
60x120 A E X T R A 2 0	23 1/8"x47 1/8"	1	0,72	~31,14	36	25,2	~1089,90
60x60 A E X T R A 2 0	23 1/8"x23 1/8"	2	0,72	~31,33	30	21,60	~939,90

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz

· Tile Performance Data · Caractéristique Technique · Technische Daten · Материал для ваших проектов

Classificazione secondo EN 14411 ISO 13006 annesso G gruppo Bla con Ev ≤0,5 % - Classification in accordance with EN 14411 ISO 13006 annex G standards Bla with Ev ≤ 0,5% - Classification selon EN 14411 ISO 13006 annexe G groupe Bla avec Ev ≤0,5% - Klassifizierung gemäß EN 14411 ISO 13006 anlage G Gruppe Bla mit Ev ≤0,5% - Классификация в соответствии с EN 14411 ISO 13006, приложение G, стандарт Bla, где Ev ≤0,5%

Caratteristica Tecnica Tile Performance Data Caractéristique Technique Technische Daten Техническая Характеристика		Metodo di prova Tests method Méthode d'essai Testmethode Метод испытания		Valore * Medio * Caesar* - Average *Caesar* Value * - Valeur * Moyen * Caesar* *Caesar* Durchschnittswert * - Среднее Значение *Caesar* *	
				Matt - Grip	A E X T R A 2 0
	Dimensione - Size Dimension - Abmessungen - Размер	ISO 10545-2	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует	
	Assorbimento d'acqua* - Water absorption* Absorption d'eau* - Wasseraufnahme* - % Поглощения воды*	ISO 10545-3	≤ 0,1%	≤ 0,1%	
	Resistenza alla flessione* - Bending strength* Résistance à la flexion* - Biegezugfestigkeit* - Упругость*	ISO 10545-4	Conforme - In accordance Conforme - Erfüllt - Соответствует	Non applicabile a piastrelle con una forza di rottura Not applicable to tiles with a breaking strength N'est pas applicable aux carreaux avec une charge de rupture Nicht anwendbar bei Fliesen mit einer Bruchlast Не применяется в отношении плиток с прочностью на разрыв ≥ 3000 N	
	Sforzo di rottura (S) - Breaking strength Charge de rupture - Bruchlast - Ударопрочность	ISO 10545-4	Sps ≥ 7,5 mm S ≥ 1300 N	> 10.000 N	
	Resistenza all'abrasione profonda* - Deep scratch resistance* Résistance à l'abrasion profonde* - Widerstand gegen Tiefenverschleiß* - Устойчивость к глубокому истиранию*	ISO 10545-6	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует	
	Coefficiente di dilatazione termica lineare* Thermal linear expansion coefficient* Coefficient de dilatation thermique linéaire* Koeffizient der linearen thermischen Dehnung* Коэффициент линейного термического расширения*	ISO 10545-8	≤ 7 (10 ⁻⁶ °C ⁻¹)	= 7 (10 ⁻⁶ °C ⁻¹)	
	Resistenza agli sbalzi termici* - Thermal shock resistance* Résistance aux écarts de température* - Temperaturwechsel Beständigkeit* - Устойчивость к термическому перепаду*	ISO 10545-9	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	
	Dilatazione all'umidità* - Expansion in humidity* Dilatation à l'humidité* - Feuchtigkeitsausdehnung* Расширение в условиях влажности*	ISO 10545-10	≤ 0,1 (mm/m)	≤ 0,1 (mm/m)	
	Resistenza al gelo* - Frost resistance* Résistance au gel* - Frostbeständigkeit* - Морозостойкость*	ISO 10545-12	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	
	Resistenza all'attacco chimico* - Resistance to chemical attack* - Résistance à l'attaque chimique* - Beständigkeit gegen Chemikalien* - Устойчивость к химическому воздействию*	ISO 10545-13	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	
	Carico statico - Static load Charge statique - Statische Last Статическая нагрузка	EN 12825	-	60x60 60x120 KN>7,0 KN>5,0 Centro - Centre Au centre - Mitte - По центру Centro lato - Side centre Au centre latéralement - Mitte Seite - По центру грани Diagonale - Diagonal En diagonale - Diagonal - По диагонали KN>5,0 KN>4,0 KN>8,0 KN>7,0	
	Classe di carico di rottura*** - Breaking load class*** Classe de charge de rupture*** - Bruchlastklasse*** Класс стойкости к разрывающей нагрузке***	EN 1339	-	U11 *** T11 ***	
	Resistenza alle macchie* - Resistance to stains* Résistance aux taches* - Fleckenbeständigkeit* Устойчивость к образованию пятен*	ISO 10545-14	Pulibile - Cleanable Nettoyable - Leicht zu reinigen - Чистящийся	Pulibile - Cleanable Nettoyable - Leicht zu reinigen - Чистящийся	
	Resistenza allo scivolamento** - Slip resistance** Résistance au glissement** - Rutschhemmende Eigenschaft** Соппротивление скольжению**	EN 16165-B EN 16165-A ▲ ANSI A326.3	120x278 R9 Matt R10 B Matt WET DCOF ≥0,42	R11 C Grip WET DCOF ≥0,55	R11 C WET DCOF ≥0,55
	Spessore nominale - Nominal Thickness Épaisseur nominale - Nominalstärke Номинальная толщина		6 mm 120x278 9 mm 120x120 - 60x120 - 80x80 - 60x60 - 30x60 - 30x30	20 mm	

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz

Fire Resistance

The building code relating to fire rating regulations and standards requires specifiers to provide documentation such as fire certificates for materials used in construction.

Ceramics are in itself a fire-resistant material, mostly being manufactured at over 1200 degrees Celsius. Testing and providing such certification are therefore not relevant to the Ceramics industry.

Ceramic and Porcelain tiles are an inert material, and therefore non-combustible. They do not release fumes or toxic gases in the event of a fire. Porcelain tiles contain no sealants, waxes or other chemicals that could release VOC's into the environment. Ceramics do not pose a risk of spreading or intensifying a fire therefore there is no testing required as they do not contribute to a fire.

EXTRAORDINARY EFFECTS DURING USE PHASE:

Fire: According to /EN 13501-1:2007+A1:2009/, ceramic tiles can be classified as A1 class of fire resistance rating, because they do not contribute to fire.

It has been demonstrated that the coating of the ceramic tiles, in case of fire, reduces heat on them and thus the risk of collapse.

Water: Ceramic tiles cannot react with water because they are an insoluble material.

For further information on the physio-characteristics of fire resistance for tiles please refer to the Technical Documents section on euroceramics.co.nz

Manufacturer Details:
European Ceramics Approved
BPIR COMPLIANT

Importer Details:
European Ceramic Tiles Ltd
Address: 7A Cowley Place, Rosedale, AKL 0632
NZBN: 9429037294571
Website: euroceramics.co.nz